

A111

PAPER LABELS

Front material

Self-adhesive	Rolls	Rolls				
Face	Reflagi	Reflagloss				
Product	Off ma	Off machine, glossy, coated art paper				
Use	For hig	For high quality labels with multi-color printing and high gloss finish.				
Typical technical values						
Substance	80	g/m2	ISO 536			
Caliper	64	μm	ISO 534			
Tensile strength MD	4.8	kN/m	ISO 1924/1			
Tensile strength CD	2.7	kN/m	ISO 1924/1			
Brightness	90	%	ISO 2470/1			
Roughness	0.5	microns	ISO 8791	PPS 10		
Opacity	87	%	ISO 2471			
Gloss	90	%	Hunter 75°			
Stiffness MD	0.22	mNm	ISO/DP 2493			
Stiffness CD	0.10	mNm	ISO/DP 2493			
Printability	Suitabl	Suitable for thermal transfer printing with wax/resin ribbons.				
Sustainability	Produc	Products named as PEFC are registered to CH11/1264.00 100% PEFC certified.				

Adhesive

Adhesive	Perma	Permanent adhesive			
Composition	Rubbe	Rubber, hotmelt			
Use	initial a	Recommended for use in cold environment, particularly if the application surface is moist or if very high initial adhesion is required. Good low temperature performance once labelled. Very good adhesion to non-polar surfaces.			
Typical technical values					
Tack min	14	N	FTM 9		
Shear min	3.0	h	FTM 8		
PE-looptack min	10	N	modified FTM 9		
Labelling temperature min	-5	°C			
Service temperature min	-40	°C			
Service temperature max	50	°C			
Limitations	Not su	Not suitable for labelling of plasticised PVC.			



Approvals	The raw materials conform to FDA 21CFR 175.105 (indirect food contact). The research centra ISEGA has given the approval for direct contact with dry and moist non-fatty foods.	
Shelf life	Two years from the date of manufacture in +20°C and RH 50%.	

Backing

Self-adhesive	Rolls				
Backing	Glassine	Glassine			
Product	Yellow transparent glassine backing paper				
Use	Backing paper for all reelstock applications; suitable for automatic dispensing.				
Typical technical values					
Substance	60	g/m2	ISO 536		
Caliper	53	microns	ISO 534		
Tensile strength MD	190.0	N/mm ²	DIN 53455		
Tensile strength CD	200.0	N/mm ²	DIN 53455		

Food contact regulations

We hereby confirm that the above mentioned product is in compliance with the EC regulations

EC 1935/2004 on materials and articles intended to come into contact with food.

EC 2023/2006 on good manufacturing practice for materials and articles intended to come into contact with food.

Furthermore most of the components are in compliance with the following regulations

EU~10/2011~on~plastic~materials~and~articles~intended~to~come~into~contact~with~food~with~the~following~restrictions:

FCM number	CAS number	Substance name		Restrictions*	
384	991-84-4	2,4-Bis(octylmerapto)-6(4-hydroxy-3,5-di-terttertbytylanilo)-1,3,5-triazine	SML	30 mg/kg	
756	110553-27-0	2,4-Bis(octylthiomethyl)-6-Methylphenol	SML(T)	5 mg/kg	

Those components that are not listed in EU 10/2011 on plastic materials and articles intended to come into contact with food are in compliance with the following regulations.

"Verpakkingen - en Gebruiksartikelenbesluit (Warenwet) 01.10.1979" published in the "Nederlandse Staatscourant" of 25.01.1980 and subsequent amendments.

Royal Decree 847/2011 of 17 June, establishing the positive list of permitted substances for the manufacture of polymeric materials intended to come into contact with food, with the same restrictions and limitations and for the same applications as authorized by The Netherlands in accordance with the principle of mutual recognition established by the Treaty on the Functioning of the European Union.





Furthermore all components are in compliance with the following regulation the Federal Drug and Cosmetic Act for the use in adhesives according to FDA Regulation 21 CFR 175.105 providing that the product is used subject to limitations found in the mentioned section.

Certificates

REACH

Please contact Altec for the latest REACH document available.

RoHS

Please contact Altec for the latest RoHS document available.

Disclaimer

Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available as is and that Altec gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.